



Date: .....

No: .....

Attachment: .....

## Apafeed petrochemical trading LLC

### Base Oil SN350

Properties	Unit	Min.	Typical	Max.	Test Method
Kinematic Viscosity @40°C	cSt	–	75	–	ASTM D 445
Kinematic Viscosity @100°C	cSt	8.3	–	9.3	ASTM D 445
Viscosity Index		95	–	–	ASTM D 2270
Flash Point (COC)	°C	220	–	–	ASTM D 92
Pour Point	°C	–	–	-6	ASTM D 97
CCR	%Wt	–	0.06	–	ASTM D 189
Total Acidity	mgKOH/g	–	–	0.05	ASTM D 664
Demulsibility		–	Pass	–	ASTM D 1401
Sulfur Content	%Wt	0.15	–	0.6	ASTM D 1552
Color		–	2	1	ASTM D 1500
Density @15°C	kg/m <sup>3</sup>	–	880	–	ASTM D 1298
Copper Corrosion, 3 hrs @100°C		–	–	1A	ASTM D 130
Foam	ml	–	Nil	–	ASTM D 892